

General Product Information:

ROXUL® products are mineral wool fibre insulations made from basalt rock and slag. This combination results in a non-combustible product with a melting point of approximately 2150°F (1177°C), which gives it excellent fire resistance properties. ROXUL mineral wool is a water repellent yet vapour permeable material.

Description & Common Applications:

ROXUL Safe® product is a non-combustible, lightweight and water repellent semi-rigid insulation batt that provides fire stopping and acoustical insulation properties. Specifically engineered and produced as a fire stopping material for commercial, industrial and residential buildings, Roxul Safe can be used for the following applications:

- perimeter gaps between concrete floor slabs and exterior wall systems,
- around conduit pipe and duct openings through walls and floor slabs,
- between fire walls and ceiling slabs.

This product has excellent fire performance properties, such as high melt temperature and low thermal conductivity which means the insulation acts as a shield against fire and temperature. In addition, Roxul products are subject to very little shrinkage in the critical phase of a fire, so the insulation layers remain in place to better prohibit the spread of flame. Roxul Safe is intended to be used in conjunction with a fire sealant to prevent the passage of fire and smoke.

Compliance and Performance:

CAN4 - S115M	Standard Test Method of Firestop Systems	Complies
ASTM C 612	Mineral Fiber Block and Board Thermal Insulation	Type IVA, Complies
MEA Approval	New York City Approval	339-97-M
City Of Los Angeles Approval		RR 25444
UL Design Nos.	Consult UL Directory for numerous approved fire rated joint systems, through penetration designs and curtain wall design listings, or contact Roxul for further information.	

Fire Performance:

ASTM E 136	Behaviour of Materials at 750°C (1382°F)	Non-Combustible
CAN4 S114	Test for Non-Combustibility	Non-Combustible
ASTM E119 (UL 263)	Standard Test Methods for Fire Tests of Building Construction and Materials	Approved
ASTM E 84(UL 723)	Surface Burning Characteristics	Flame Spread = 0 Smoke Developed = 0
CAN/ULC S102	Surface Burning Characteristics	Flame Spread = 0 Smoke Developed = 0

Smoulder Resistance:

CAN/ULC-S129	Smoulder Resistance	0.01%
--------------	---------------------	-------

Moisture Resistance:

ASTM C 1104	Moisture Sorption	0.04%
-------------	-------------------	-------

Corrosive Resistance:

ASTM C 665	Corrosiveness to Steel	Pass
ASTM C 795 ****	Stainless Steel Stress Corrosion Specification as per Test Methods C871 and C692: U.S. Nuclear Regulatory Commission, Reg. Guide #1.36: U.S. Military Specifications MIL-I-24244 (all versions including B and C)	Conforms

Acoustical Performance

Thickness	ASTM C423 CO-EFFICIENTS AT FREQUENCIES						NRC
	125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	
2.0	0.26	0.68	1.12	1.10	1.03	1.04	1.00
3.0	0.63	0.95	1.14	1.01	1.03	1.04	1.05
4.0	1.03	1.07	1.12	1.04	1.07	1.08	1.10

Compressive Strength:

ASTM C 165 at 10% 144 psf (6.9 kPa)

Density:

ASTM C 612-00 Actual 4.5 lbs/ft³ 72 kg/m³

Dimensions:

24" (width) x 48" (length)
610 mm (width) x 1219 mm (length)

Thickness:

Product thickness is available in 2", 3" and 4"

For additional sizes, please contact our customer service representatives.

Facing:

This product can be faced with reinforced foil facing. Please note that the facings will influence the product's service temperature range.

Key Application Qualifiers:

- Easily cut
- Non-combustible
- Excellent sound absorbency
- Chemically inert
- Does not rot or sustain vermin
- Does not promote growth of fungi or mildew
- Low moisture sorption
- Water resistant
- CFC and HCFC free product and process
- Made from natural & recycled materials

Other ROXUL Products:

Please consult ROXUL for all your insulation needs. We have an extensive range of products for all applications from pipe insulation to commercial products to residential batts. ROXUL invites all inquiries and will act promptly to service all of your requirements.



**** "Provisions for lot testing may be required, consult manufacturer."

Note:

As ROXUL Inc. has no control over installation design and workmanship, accessory materials or application conditions, ROXUL Inc. does not warranty the performance or results of any installation containing ROXUL Inc's. products. ROXUL Inc's. overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

ROXUL INC.
www.roxul.com

Milton, Ontario Tel: 905-878-8474
Tel: 1-800-265-6878

Fax: 905-878-8077
Fax: 1-800-991-0110

Revised: December 14, 2011
Supersedes: May 25, 2009